



# FULLER TRADE PLUMBING SILICONE

### Description

Fuller Trade Plumbing Silicone is a neutral cure silicone sealant which does not corrode materials commonly used in roofs and gutters.

### Benefits

- Tested by the Australian Water Quality Centre and meets the requirements of AS4020-1999, Products for Use in Contact with Drinking Water.
- Permanently flexible
- Water resistant
- UV and weather resistant
- Resistant to temperature extremes: -50°C to 150°C
- 25% dynamic movement capability
- One part, ready to use
- 25 year guarantee against cracking and crumbling when used in standard conditions and applications.

### Uses

- Used in sheet metal and aluminium roofing applications
- Exterior cladding
- Guttering
- Flashing
- Downpipes

Steel	Stainless Steel
Galvanised iron	Aluminium
Ceramic tiles	Masonry
Lead	Terracotta
Glass	Zincalume
Fiberglass	Most plastics (pretest)

### Compatible Substrates

### Coverage

300ml cartridge will give approximately 15 lineal metres of a 5mm bead

### Performance Data

Property	Data
Specific Gravity	1.02 Translucent / 1.3 Grey
Sag	Nil
Tooling Time	5 minutes
Skinning Time	5-10 min, 25°C, 50% RH
Full Cure	After 7 days
Service Temperature	-50°C to 150°C
Water Immersion	Not suitable
Joint Movement	+ 25%
Hardness	19 Shore A trans, 26 grey

### Limitations

- Not for structural glazing
- Not suitable for use below ground
- Not for permanent or continuous water immersion
- Not recommended as a plug or seal on burst water pipes or rusted guttering
- Pre test on coated surfaces to establish suitability

## Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

**Australia**  
Tel: +61 1800 423 855  
customer.service@hbfuller.com  
**China & Hong Kong**  
Tel: +86 20 82068291  
cs.china@hbfuller.com  
**Indonesia**  
Tel: +62-21-5307232/33

**Korea**  
Tel: +82 2 786 8296  
cskorea@hbfuller.com  
**Malaysia**  
Tel: +603 3345 5200  
**New Zealand**  
Tel: +64 800 555 072  
customer.service@hbfuller.com

**Philippines**  
Tel: +63 2 5194073  
**Taiwan**  
Tel: +886 2 26033385  
**Thailand**  
Tel: +66 2 3757442  
**Vietnam**  
Tel: +84 8 2225588



- Do not use on marble or other highly porous stone - finish may be affected
- Do not use on copper or brass as discolouration may occur
- Powder coated metal surfaces may have high wax contents. Ensure that these surfaces are solvent cleaned. Pre test silicone to ensure adhesion to surface
- Not recommended in situations where movement exceeds  $\pm 25\%$  of the original joint dimensions
- Maximum joint depth 20mm
- Not suitable for use where high abrasion, e.g. foot traffic is expected
- Do not use to construct aquariums
- Do not use on materials that bleed oils, plasticisers or solvents as this will affect adhesion
- Not a fire rated sealant
- Do not use in direct contact with silver coating of mirrors (e.g. on the edge of the mirror)

### Surface Preparation

All surfaces must be clean, dry, sound and free of dust, oil, old sealant or other contamination.

Lightly contaminated surfaces should be wiped with isopropyl alcohol (IPA) using the 2-rag wipe method. Apply IPA to a clean lint-free cloth and wipe onto the surface to be cleaned to solubilise and remove the majority of the contaminant. A clean dry cloth should then be applied to remove remaining contamination and dry the surface. Ensure wet cleaner is not allowed to dry on surface. For more heavily contaminated surfaces or where the IPA does not remove the contaminant, a generic wax and grease remover should be applied using the same 2-rag wipe method. Once this has been completed the surface should be given a final

clean with IPA using the 2-rag wipe method to ensure the surface is adequately prepared. Adhesion to metals and some surface finishes can be further improved by light abrasion prior to cleaning with IPA using the 2 rag-wipe method. For glazing applications IPA should be used to clean and prepare the surface. Manufacturers of plastics should be consulted about suitable cleaning solvents. Adhesion to plastics should be pre-tested. Mask either side of joint to produce a neat finish. Use a suitable sized foam backing rod or polyethylene bond breaker tape to prevent three sided joint contact impeding the free and even deformation of the sealant in a cyclic joint.

### Product Application

Cut seal on top of cartridge. Screw on nozzle and cut to desired bead size. Hold gun at 45° angle. Push forward, squeezing trigger to gently fill joint. Within 5 minutes of application tool the sealant, ensure the sealant wets the sides of the joint. If masking tape is used to produce a neat finish, remember to remove the masking tape before the sealant skins. Trim with a knife once cured, if needed.

### Painting

Mask all areas not requiring sealant. Paint will not adhere to silicone. Complete any painting and allow to thoroughly dry before applying sealant.

### Chemical Resistance

Resistant to water, salt water, grease, oils, fuels, defrosting liquid, detergents, aliphatic fats, mildew, weak acids and bases (pre testing required).

## Our Focus is Clear. Perfecting Adhesives.

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

**Australia**  
Tel: +61 1800 423 855  
customer.service@hbfuller.com  
**China & Hong Kong**  
Tel: +86 20 82068291  
cs.china@hbfuller.com  
**Indonesia**  
Tel: +62-21-5307232/33

**Korea**  
Tel: +82 2 786 8296  
cskorea@hbfuller.com  
**Malaysia**  
Tel: +603 3345 5200  
**New Zealand**  
Tel: +64 800 555 072  
customer.service@hbfuller.com

**Philippines**  
Tel: +63 2 5194073  
**Taiwan**  
Tel: +886 2 26033385  
**Thailand**  
Tel: +66 2 3757442  
**Vietnam**  
Tel: +84 8 22225588

**Curing**

The rate of cure depends on the air temperature and humidity, the cross sectional area of the bead of sealant and the surface area of sealant exposed to the air. At 25°C and 50% relative humidity cure rate is 2 mm / 24 hours. In general, low humidity and/or low temperature will result in longer cure times. Thicker sections of sealant will have longer cure times. A small surface area in relation to the volume of sealant will also extend the cure time. Ensure that the depth of the sealant in a joint never exceeds its width.

downloadable from the HB Fuller web site,  
[www.hbfuller.com.au](http://www.hbfuller.com.au)

**Shelf Life**

Fuller Trade Plumbing Silicone will remain suitable for use for 12 months from date of manufacture, if stored in original container, unopened, in cool dry place in temperatures less than 30°C. Once opened, the contents should be used as soon as possible. The life of contents of an opened cartridge can be extended if the nozzle is left in place after use and the tip is wrapped in plastic film.

**Clean Up**

Best results are obtained by masking prior to sealing to avoid the necessity for clean up. However, if sealant is applied to areas where it is unwanted, clean up uncured sealant using toluene\*, xylene\*, methyl ethyl ketone\*, or mineral turpentine\* and a cloth. Cured sealant should be removed by abrasion or trimmed with a sharp knife. Do not undercut seal.

**Safety Information**

A Material Safety Data Sheet is available from the H.B. Fuller representative your state, HB Fuller Australia customer service, or

Version 2  
TDS Date: 16/03/2023

**Our Focus is Clear. Perfecting Adhesives.**

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence or for death or personal injury caused by negligence or for breach of any mandatory implied terms.

**Australia**  
Tel: +61 1800 423 855  
customer.service@hbfuller.com  
**China & Hong Kong**  
Tel: +86 20 82068291  
cs.china@hbfuller.com  
**Indonesia**  
Tel: +62-21-5307232/33

**Korea**  
Tel: +82 2 786 8296  
cskorea@hbfuller.com  
**Malaysia**  
Tel: +603 3345 5200  
**New Zealand**  
Tel: +64 800 555 072  
customer.service@hbfuller.com

**Philippines**  
Tel: +63 2 5194073  
**Taiwan**  
Tel: +886 2 26033385  
**Thailand**  
Tel: +66 2 3757442  
**Vietnam**  
Tel: +84 8 2225588